Appl. No. 10/698,143

Amdt. dated August 30, 2005

Reply to Office action of June 14, 2005

In the Claims:

Claims 1-26 are canceled. New claims 27-29 are added.

1-26. (canceled)

27. (new) A method for fabricating a reflective type reflector plate of a reflective liquid crystal display, the method comprising the steps of:

preparing a glass substrate with thin film transistors built on a surface of the glass substrate;

forming transparent electrodes over the glass substrate
after the thin film transistors are built on the glass substrate;
depositing a protection layer over the transparent

electrodes;

patterning the transparent electrodes and the protection layer to form pixel patterns;

spin coating a photoresist layer over the protection layer using polymer resin material;

removing the photoresist layer over non-patterned areas; and depositing a reflective metal film over the photoresist layer retained on the glass substrate;

wherein after the protection layer is deposited over the transparent electrodes, the protection layer shields undesired reflection light during an exposure stage and reduces the exposure time.

Page 3 — RESPONSE (U.S. Patent Appln. S.N. 10/698,143) [\\Files\files\Correspondence\August 2005\t1270rtoa083005.doc]

Appl. No. 10/698,143

Amdt. dated August 30, 2005

Reply to Office action of June 14, 2005

- 28. (new) The method as claimed in claim 27, wherein the protection layer is metal material.
- 29. (new) The method as claimed in claim 27, wherein the protection layer is non-metal material.

Page 4 — RESPONSE (U.S. Patent Appln. S.N. 10/698,143) [\\Files\files\Correspondence\August 2005\t1270rtoa083005.doc]